

TÔLES EN ALLIAGE EN AW-2017A											
Etat	Epaisseur spécifiée (mm)		Rm (MPa)		Rp0,2 (MPa)		A % mini		Rayon de pliage		Dureté HBS
	supérieure à	jusqu'à	mini	maxi	mini	maxi	A 50	A	180°	90°	
O	≥ 0,4	1,5		225		145	12				55
	1,5	3,0		225		145	14			0 e	55
	3,0	6,0		225		145	13			1,0 e	55
	6,0	9,0		225		145	13		0,5 e	1,5 e	55
	9,0	12,5		225		145	13		1,0 e	2,5 e	55
	12,5	25,0		225		145		12		4,0 e	55
T4 T451 (1)	≥ 0,4	1,5	390		245		14		3,0 e	3,0 e	110
	1,5	6,0	390		245		15		5,0 e	5,0 e	110
	6,0	12,5	390		260		13			8,0 e	111
T451	12,5	40,0	390		250			12			110
	40,0	100,0	385		240			10			108
	100,0	120,0	370		240			8			105
	120,0	150,0	350		240			4			101
T42	≥ 0,4	3,0	390		235		14				109
	3,0	12,5	390		235		15				109
	12,5	25,0	390		235			12			109

Tableau 51